



	Weight [g/m ²]	Thickness [µm]	Opacity [%]	CIE Lab		
				L*	a*	b*
EFI Proof Paper 5120 Matt	120	145	96	94,0	3,0	-7,5
EFI Proof Paper 5125 DUO-Matt	125	165	97	94,0	3,0	-7,5
EFI Proof Paper 9120 Matt	120	150	95	97,0	1,3	-2,5
EFI Proof Paper 9190 Matt	190	225	98	97,0	1,3	-2,5
EFI Budget Proof Paper 3170 Semimatt	165	190	97	95,0	3,5	-7,0
EFI Proof Paper 9150 Semimatt	150	150	93	95,5	0,6	-2,3
EFI Proof Paper 9155 DUO-Semimatt	170	200	96	95,5	0,6	-2,3
EFI Remoteproof Paper 9180 Semimatt	180	200	95	95,5	0,6	-2,3
EFI Gravure Proof Paper 4245 Semimatt	245	260	96	94,8	0,3	-1,5
EFI Packaging Proof 9380 Semimatt	380	445	99	96,5	-0,1	-3,0
EFI Proof Paper 8180 Semiglossy	180	190	94	97,0	-0,1	-3,3
EFI Proof Paper 4200 Glossy	200	190	94	94,8	-0,2	-3,8
EFI Proof Paper 5150 Glossy	150	170	96	93,8	2,4	-6,0
EFI Proof Paper 5180 Heavy-Gloss	180	220	97	93,8	2,4	-6,0
EFI Proof Paper 7180 Glossy	180	190	94	97,0	-0,1	-3,3
EFI Proof Paper ZP 55 (Newspaper)	55	80	92	88,5	-0,5	4,8
EFI Laser Paper Matt 92M	92	98	92	94,0	1,8	-9,0
EFI Laser Paper Matt 162M	162	166	96	94,7	2,0	-10,0
EFI Laser Paper DUO-Semimatt 105SM	105	103	92	93,0	1,0	-1,7
EFI Laser Paper DUO-Semimatt 130SM	130	140	92	93,5	1,0	-1,3
EFI Laser Paper Glossy 162GL	162	183	97	95,0	-0,3	-0,6
EFI Laser Paper Glossy 205GL	205	230	99	95,0	-0,3	-0,4
EFI Photo Paper 1250 Semimatt	250	260	96	95,0	-0,2	-3,6
EFI Photo Posterboard 8600 Semiglossy	600	750	99	96,0	1,4	-8,0
EFI Photo Paper 1240 High-Gloss	270	250	97	95,8	0,7	-4,5
EFI Photo Paper 4250 Premium High-Gloss	250	280	96	94,5	-0,2	-4,1
EFI Photo Fine Art 'Handmade' Water Color Paper	140	230	94	96,6	-0,7	4,5
EFI Photo Fine Art Water Color Paper	230	355	99	97,0	0,3	3,0
EFI Photo Fine Art Canvas	330	520	99	96,0	-0,3	0,8

All Paper White Points measured with Best.Eye, from different lots and charges, same procedure with Gretag Spectrolino. Each value is an average about minimum 15 measurements.